

Paul M. Wolff Co. Chemical Resistance Chart

KEY TO CHEMICAL RESISTANCE CHART

Rating	Meaning
A	Not recommended for exposure to this chemical
B	Short term exposure splash spill (recommended for exposure times not to exceed 2 hours)
C	Long term exposure splash spill (recommended for exposure not to exceed a normal 8-10 hour work shift without cleanup)
D	Short term immersion (recommended for exposure not to exceed 72 hours)
E	Long term immersion (recommended for continuous exposure to chemical. Life expectancy is variable. Long term exposures such as a tank linings and trenches fall under this rating.)
T	This rating is used to depict chemicals that do not have any service data; but based on technical knowledge are suitable for exposure to this chemical *denotes 12 hour heat cure at 150°F

Many chemicals for corrosive environments are represented in the following chemical chart. Much of the information is from actual lab testing or field experience established during our many years of business. In some instances where neither field service nor laboratory testing has contributed to the classification, our chemists have rated the chemicals according to expected characteristics. However, many applications are complicated by mixtures of chemicals, temperature fluctuations and other intricate conditions existing at the specific job site. For these reasons, it is advisable to place a test patch prior to the installation of any product to investigate the suitability of your selection with your specific needs. When other questions arise concerning any chemical matters, feel free to contact your sales agent for further information. Details for application guidelines are also available from your sales agent upon request.

	Epoxy-O-Sheen F	Epoxy-O-Sheen	Ure-Sheen W	Epoxy-O-Sheen 100C	Ure-Sheen	Ure-Sheen CRU	Ure-Sheen CRU	Epoxy-O-Sheen 100P	Shur-Fill
			(VOC Compliant in CA) Clear Only	(C= Clear; only comes in clear for decorative sys)	(not VOC Compliant in CA)	(not VOC Compliant in CA)	(CA)	(P= Pigmented, for colored top coats) OR Epoxy-O-Sheen HS	(Only to be used under a coating)
ACETALDEHYDE	B	B	A	C	C	C	C	C	B
ACETIC ACID 5%	B	B	A	B	C	B	C	C	A
ACETIC ACID 10%	A	A	A	A	B	B	B	B	A
ACETIC ACID 25%	A	A	A	A	A	A	A	A	A
ACETIC ACID GLACIAL	A	A	A	A	A	A	A	A	A
ACETIC ANHYDRIDE	A	A	A	B	C	C	C	B	A
ACETONE 10%	B	B	A	B	B	B	B	C	B
ACETONE 100%	A	A	A	B	B	B	B	B	A
ACETYL CHLORIDE	A	A	A	A	TB	TB	TB	A	A
ACETONITRILE	B	B	A	B	C	C	C	B	B
ACRYLIC ACID	A	A	A	TB	TB	TB	TB	TB	A
ACRYLONITRILE	A	A	A	TB	A	A	A	TB	A
ADIPIC ACID 25%	B	B	A	B	B	B	B	B	B
ALLYL ALCOHOL	TB	TB	A	TC	TC	TC	TC	TC	TB
ALLYL CHLORIDE	A	A	A	TB	TB	TB	TB	TB	A
ALUMINUM BROMIDE	C	C	B	D	D	D	D	D	C
ALUMINUM CHLORIDE	TC	TC	B	TC	TD	TD	TD	TC	TC
ALUMINUM FLUORIDE	TC	TC	B	TC	TB	TB	TB	TC	TC
ALUMINUM HYDROXIDE	C	C	B	C	C	C	C	C	C
ALUMINUM NITRATE	C	C	B	D	C	C	C	D	C
ALUMINUM SULFATE	B	B	A	C	C	C	C	C	B
AMMONIA	C	C	B	D	D	D	D	D	C
AMMONIUM CHLORIDE	TB	TB	A	TC	TC	TC	TC	TC	TB
AMMONIUM FLUORIDE	TB	TB	A	TB	TB	TB	TB	TB	TB
AMMONIUM HYDROXIDE	TB	TB	A	TC	TC	TC	TC	TC	TB
AMMONIUM NITRATE	C	C	B	D	D	D	D	D	C
AMMONIUM OXALATE	C	C	B	C	C	C	C	C	B
AMMONIUM NITRATE AMMONIUM PERSULFATE	TC	TC	TB	TD	TD	TD	TD	TD	TC
AMMONIUM PHOSPHATE	B	B	A	C	C	C	C	C	B
AMMONIUM SULFATE	C	C	B	D	C	C	C	D	B
AMMONIUM SULFIDE	C	C	B	D	C	C	C	D	C
AMMONIUM SULFITE	C	C	B	D	C	C	C	D	C
AMYL ACETATE	TB	TB	A	TC	TB	TB	TB	TC	TB
AMYL ALCOHOL	B	B	A	C	C	C	C	C	B
ANILINE ANILINE HYDROCHLORIDE	A	A	A	B	B	B	B	B	A
ANTIMONY CHLORIDE	A	A	A	TB	TB	TB	TB	TB	A
AQUA REGIA	A	A	A	A	A	A	A	A	A
ARSENOUS ACID	A	A	A	TB	TB	TB	TB	TB	A
BARIUM ACETATE	B	B	A	C	C	C	C	C	A
BARIUM BROMIDE	B	B	A	C	B	B	B	C	B
BARIUM CARBONATE	B	B	A	C	B	B	B	C	B
BARIUM CHLORIDE	B	B	A	B	D	D	D	C	B
BARIUM HYDROXIDE	TB	TB	A	TC	TC	TC	TC	TC	TB
BARIUM SULFATE	B	B	A	C	C	C	C	C	B
BARIUM SULFIDE	A	A	A	C	B	B	B	C	A
BENZYL CHLORIDE	A	A	A	TB	TB	TB	TB	TB	A
BENZOIC ACID	B	B	A	C	B	B	B	C	B
BENZALDEHYDE	A	A	A	TB	TB	TB	TB	TB	A
BENZENE	TB	TB	A	TC	TB	TB	TB	TC	TB
BENZYL ALCOHOL	B	C	B	B	C	C	C	D	C
BLACK LIQUOR (PAPER)	TB	TB	A	TC	TC	TC	TC	TC	TB
BLOOD SUGAR	TB	TB	A	TC	TC	TC	TC	TC	TB
BORAX	B	B	A	C	C	C	C	C	B
BORIC ACID	A	A	A	C	B	B	B	C	A

	Epox-O-Sheen F	Epox-O-Sheen	Ure-Sheen W (VOC Compliant in CA) Clear Only	Epox-O-Sheen 100C (C= Clear; only comes in clear for decorative sys)	Ure-Sheen (not VOC Compliant in CA)	Ure-Sheen CRU (not VOC Compliant in CA)	Ure-Sheen CRU (CA)	Epox-O-Sheen 100P (P= Pigmented, for colored top coats) OR Epox-O-Sheen HS	Shur-Fill (Only to be used under a coating)
BRINE	D	D	B	D	D	D	D	D	D
BROMINE LIQUID	A	A	A	A	A	A	A	A	A
BUTANOL	C	C	B	C	D	D	D	D	C
BUTYL ACETATE	B	B	A	C	C	C	C	C	B
BUTYL ACRYLATE	A	A	A	TB	TB	TB	TB	TB	A
BUTYL AMINE	A	A	A	TB	TB	TB	TB	TB	A
BUTYL CARBITOL	TB	TB	A	TC	TC	TC	TC	TC	TB
BUTYL CELLOSOLVE	B	B	A	C	B	B	B	C	B
BUTYL ETHER	B	B	A	C	B	B	B	C	B
BUTYRIC ACID	A	A	A	A	B	B	B	A	A
CALCIUM BISULFITE	C	C	B	D	D	D	D	D	C
CALCIUM BROMIDE	TB	TB	A	TC	TC	TC	TC	TC	TB
CALCIUM CARBONATE	B	B	A	C	C	C	C	C	B
CALCIUM CHLORATE	B	B	A	C	C	C	C	C	B
CALCIUM CHLORIDE	C	C	B	D	D	D	D	D	C
CALCIUM HYDROXIDE	B	B	A	D	C	C	C	D	B
CALCIUM HYPOCHLORITE	A	A	A	TB	TC	TC	TC	TB	A
CALCIUM NITRATE	C	C	B	D	D	D	D	D	C
CALCIUM SULFATE	B	B	A	C	C	C	C	C	B
CALCIUM SULFITE	B	B	A	C	C	C	C	C	B
CALCIUM DISULFIDE	A	A	A	B	B	B	B	B	A
CARBON TETRACHLORIDE	B	B	A	B	C	C	C	C	B
CASTOR OIL	B	B	B	C	D	D	D	C	B
CELLOSOLVE	TB	TB	A	TC	TC	TC	TC	TC	TB
CELLOSOLVE ACETATE	B	B	A	C	C	TC	C	C	B
CHLOROACETIC ACID	A	A	A	A	A	C	A	B	A
CHLOROACETIC ACID 25%	A	A	A	A	A	A	A	A	A
CHLOROACETIC ACID 50%	A	A	A	A	A	A	A	A	A
CHLOROBENZENE	B	B	A	C	B	A	B	C	B
CHLOROFORM	A	A	A	TB	A	B	A	TB	A
CHLOROPHENOL	A	A	A	A	A	A	A	A	A
CHLOROSULFONIC ACID	A	A	A	A	A	A	A	A	A
CHLOROTOLUENE	A	A	A	TB	TB	A	TB	TB	A
CHROMIC ACID 10%	A	A	A	A	B	TB	B	A	A
CHROMIC ACID 40%	A	A	A	A	A	B	A	A	A
CHROMIC CHLORIDE	A	A	A	A	A	A	A	A	A
CITRIC ACID	B	B	A	C	D	A	D	C	B
COPPER ACETATE	B	B	A	C	D	D	D	C	B
COPPER CHLORIDE	B	B	A	B	C	D	C	B	B
COPPER CYANIDE	TB	TB	A	TC	TC	C	TC	TC	TB
COPPER NITRATE	TB	TB	A	TC	TC	TC	TC	TC	TB
COPPER SULFATE	B	B	A	C	B	TC	B	C	B
CORN OIL	B	B	A	C	C	B	C	C	B
CORN STARCH SLURRY	D	D	B	E	E	C	D	E	C
CORN SUGAR	C	C	B	D	D	E	D	D	C
COTTONSEED OIL	B	B	A	C	C	D	C	C	B
CREOSOTE	B	B	A	C	C	C	C	C	B
CRESYLIC ACID	A	A	A	TB	TB	C	TB	TB	A
CUMENE	B	B	A	C	B	TB	TB	C	B
CUTTING OIL	C	C	A	C	C	B	C	C	B
CYCLOHEXANE	B	B	A	C	C	C	C	C	B
CYCLOHEXANONE	C	C	B	C	C	C	C	C	B
CYMENE	TB	TB	A	TC	TC	C	TC	TC	TB
DETERGENTS ORGANIC	TC	TC	TB	TE	TC	TC	TC	TE	TC
DETERGENTS SULFONATED	TC	TC	TB	TE	TC	TC	TC	TE	TC
DEXTRROSE	D	D	B	E	E	TC	TD	E	C
DIBUTYL PHTHALATE	C	C	B	D	D	E	D	D	C
DICHLORACETIC ACID	A	A	A	TB	TB	D	TC	TC	A
DICHLOROBENZENE	B	B	A	C	C	TB	TC	C	B
DICHLOROETHANE	A	A	A	A	B	C	B	A	A
DIESEL FUEL	B	B	A	C	C	B	B	C	B
DIETHANOLAMINE	TB	TB	A	TB	TC	C	TC	TB	TB
DIETHYL BENZENE	TB	TB	A	TC	TC	TC	TC	TC	TB
DIETHYL KETONE	A	A	A	TB	TB	TB	TB	TB	A
DIETHYLENE GLYCOL	B	B	A	C	C	C	C	C	B
DIETHYL ETHER	A	A	A	B	C	C	C	B	A
DIMETHYL ANILINE	A	A	A	TB	TB	TB	TB	TB	A

	Epoxy-O-Sheen		Ure-Sheen W (VOC Compliant in CA) Clear Only	Epoxy-O-Sheen 100C (C= Clear; only comes in clear for decorative sys)	Ure-Sheen (not VOC Compliant in CA)	Ure-Sheen CRU (not VOC Compliant in CA)	Ure-Sheen CRU (CA)	Epoxy-O-Sheen 100P (P= Pigmented, for colored top coats) OR Epoxy-O-Sheen HS	Shur-Fill (Only to be used under a coating)
	Epoxy-O-Sheen F	Epoxy-O-Sheen							
DIMETHYL FORMAMIDE	A	A	A	A	A	A	A	A	A
DIMETHYL SULFOXIDE	A	A	A	A	A	A	A	A	A
DINITRO BENZENE	A	A	A	TB	TB	TB	TB	TB	A
DINITRO TOLUENE	A	A	A	TB	TB	TB	TB	TB	A
EPICHLOROHYDRIN	B	B	A	B	B	B	B	E	A
ETHANOL	B	B	A	C	D	C	D	B	A
ETHANOLAMINE	A	A	A	B	C	C	C	B	A
ETHYL ACETATE	A	A	A	A	B	B	B	A	A
ETHYL ACRYLATE	A	A	A	A	B	B	B	A	A
ETHYLAMINE	A	A	A	A	TB	TB	TB	A	A
ETHYL BENZENE	A	A	A	TB	TB	TB	TB	TB	A
ETHYL BROMIDE	A	A	A	A	A	A	A	A	A
ETHYL CHLORIDE	A	A	A	A	A	A	A	A	A
ETHYL DICHLORIDE	A	A	A	A	A	A	A	A	A
ETHYLENE GLYCOL	C	C	B	D	D	D	D	D	C
ETHYL SULFATE	A	A	A	TB	TB	TB	TB	TB	A
FATTY ACIDS	TB	TB	A	TB	TB	TB	TB	TB	A
FERRIC CHLORIDE	D	D	B	C	E	E	E	E	C
FERRIC SULFATE	C	C	B	C	E	E	E	E	C
FERROUS NITRATE	B	B	A	C	C	C	C	C	C
FERROUS CHLORIDE	TB	TB	A	TB	TD	TD	TD	TD	TB
FERROUS SULFATE	TC	TC	TB	TD	TD	TD	TD	TE	TD
FLUOSILICIC ACID 10-25%	A	A	A	A	A	A	A	A	A
FORMALDEHYDE	B	B	A	C	B	B	B	C	B
FORMIC ACID 10%	A	A	A	B	C	C	C	B	A
FORMIC ACID 50%	A	A	A	A	A	A	A	A	A
FUEL OIL	B	B	A	C	C	C	C	C	B
FURFURAL ALCOHOL	A	A	A	TB	TB	TB	TB	TB	A
GASOLINE AVIATION	A	A	A	B	D	D	D	B	A
GASOLINE DIESEL	A	A	A	B	D	C	D	B	A
GASOLINE JET FUEL	A	A	A	B	D	C	D	B	A
GASOLINE UNLEADED	B	B	A	C	D	D	D	C	B
GLUCOSE	D	D	B	E	D	D	D	E	D
GLYCERINE	TC	TC	TB	TD	TD	TD	TD	TC	TC
GLYCOLIC ACID 70% GREEN LIQUOR (PAPER)	A	A	A	A	A	A	A	A	A
	B	B	A	C	C	C	C	C	B
HEPTANE	C	C	B	D	D	D	D	D	C
HEXANE	C	C	B	D	D	D	D	D	C
HYDRAULIC FLUID	B	B	B	C	C	C	C	C	B
HYDRAZINE 35%	A	A	A	TB	TB	TB	TB	TB	A
HYDRIODIC ACID 20%	A	A	A	B	C	C	C	C	A
HYDROBROMIC ACID 18%	A	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 40%	A	A	A	A	A	A	A	A	A
HYDROBROMIC ACID 60%	A	A	A	A	A	A	A	A	A
HYDROCHLORIC ACID 10%	B	B	B	C	D	C	D	C	C
HYDROCHLORIC ACID 36%	B	B	B	B	C	B	C	C	B
HYDROFLUORIC ACID	A	A	A	A	A	A	A	A	A
HYDROGEN PEROXIDE 10%	A	A	A	B	C	C	C	B	A
HYDROGEN PEROXIDE 50%	A	A	A	A	A	A	A	A	A
HYDROGEN SULFIDE 5%	B	B	A	C	D	D	D	C	B
HYDROGEN SULFIDE 100%	A	A	A	TC	TB	TB	TB	TC	A
HYPOCHLOROUS ACID IODINE CRYSTALS/VAPOR	A	A	A	A	A	A	A	A	A
	TB	TB	A	TC	TC	TC	TC	TC	TB
ISOPHORONE	B	B	A	C	C	C	C	C	B
ISOPROPYL ACETATE	B	B	A	C	C	C	C	C	B
ISOPROPYL ALCOHOL	B	B	A	C	C	C	C	C	B
JET FUEL (JP-4)	A	A	A	B	D	C	D	B	A
KEROSENE	B	B	A	C	C	C	C	C	B
LACTIC ACID 10-20%	B	B	A	C	D	D	D	C	B
LACTIC ACID 50%	A	A	A	A	A	A	A	A	A
LACTIC ACID 85%	A	A	A	A	A	A	A	A	A
LAURIC ACID	A	A	A	TB	TB	TB	TB	TB	A
LEAD ACETATE	TC	TC	TB	TC	TD	TD	TD	TD	TC
LEVULINIC ACID	TB	TB	A	TC	TC	TC	TC	TC	TB
LINSEED OIL	B	B	A	B	C	C	C	B	B
LITHIUM BROMIDE	TB	TB	A	TC	TB	TB	TB	TC	TB

	Epox-O-Sheen F	Epox-O-Sheen	Ure-Sheen W (VOC Compliant in CA) Clear Only	Epox-O-Sheen 100C (C= Clear; only comes in clear for decorative sys)	Ure-Sheen (not VOC Compliant in CA)	Ure-Sheen CRU (not VOC Compliant in CA)	Ure-Sheen CRU (CA)	Epox-O-Sheen 100P (P= Pigmented, for colored top coats) OR Epox-O-Sheen HS	Shur-Fill (Only to be used under a coating)
LITHIUM CHLORIDE SAT'D	A	A	A	B	B	B	B	B	A
LITHIUM HYDROXIDE	A	A	A	A	TB	TB	TB	A	A
MAGNESIUM BISULFITE MAGNESIUM CARBONATE	B	B	A	B	C	C	C	B	B
MAGNESIUM CHLORIDE MAGNESIUM HYDROXIDE	TB	TB	A	TB	TB	TB	TB	TB	TB
MAGNESIUM NITRATE	TB	TB	A	TB	TC	TC	TC	TB	TB
MAGNESIUM SULFATE	TB	TB	A	TB	TB	TB	TB	TB	TB
MALEIC ACID	A	A	A	A	B	B	B	A	A
MANGANESE CHLORIDE	TB	TB	A	TB	TB	TB	TB	TB	TB
MANGANESE SULFATE	TB	TB	A	TB	TB	TB	TB	TB	TB
MERCURIC CHLORIDE	TB	TB	A	TB	TC	TC	TC	TC	TB
MERCUROUS CHLORIDE	TB	TB	A	TC	TC	TC	TC	TC	TB
METHANOL	A	A	A	A	B	B	B	A	A
METHYL ACETATE	A	A	A	A	B	B	B	A	A
METHYLAMYL ALCOHOL	TB	TB	A	TC	TC	TC	TC	TC	TB
METHYL BENZOATE	A	A	A	B	B	B	B	B	A
METHYL CHLORIDE	A	A	A	A	A	A	A	A	A
METHYLENE CHLORIDE	A	A	A	A	A	A	A	A	A
METHYL ETHYL KETONE METHYL ISOBUTYL KETONE	A	A	A	A	B	A	B	A	A
MILK	C	C	B	D	D	D	D	D	C
MOLASSES	C	C	B	D	D	D	D	D	C
MINERAL OILS	TB	TB	A	TC	TD	TD	TD	TC	TB
MINERAL SPIRITS	B	B	A	C	C	C	C	B	B
MOTOR OIL	C	C	B	C	C	C	C	C	C
M-PYROL	A	A	A	A	A	A	A	A	A
NAPHTHA ALIPHATIC	B	B	A	B	C	C	C	B	B
NAPHTHA AROMATIC	A	A	A	B	B	C	B	B	A
NICKEL CHLORIDE	A	A	A	A	TB	TB	TB	A	A
NICKEL NITRATE	B	B	A	B	C	C	C	B	B
NICKEL SULFATE	TB	TB	A	TB	TB	TB	TB	TB	TB
NITRIC ACID 5%	B	B	A	B	D	C	D	C	B
NITRIC ACID 30%	A	A	A	B	C	B	B	B	A
NITRIC ACID 60%	A	A	A	A	A	A	A	A	A
NITROBENZENE	A	A	A	A	TB	TB	TB	A	A
OIL SOUR CRUDE	B	B	A	C	C	C	C	C	B
OIL SWEET CRUDE	TB	TB	A	TC	TC	TC	TC	TC	TB
OLEIC ACID	A	A	A	A	B	B	B	A	A
OLEUM	A	A	A	A	A	A	A	A	A
OXALIC ACID	A	A	A	A	B	B	B	A	A
PERCHLORIC ACID	A	A	A	A	A	A	A	A	A
PERCHLOROETHYLENE	A	A	A	B	B	B	B	B	A
PHENOL 5%	A	A	A	A	B	B	B	A	A
PHENOL 85%	A	A	A	A	A	A	A	A	A
PHOSPHORIC ACID 40%	B	B	B	B	D	C	D	C	A
PHOSPHORIC ACID 85%	A	A	A	A	B	B	B	A	A
PICRIC ACID 10%	A	A	A	TB	TB	TB	TB	TB	A
POTASSIUM ACETATE	B	B	A	C	C	C	C	C	B
POTASSIUM BROMIDE	B	B	A	C	D	D	D	C	B
POTASSIUM CARBONATE	B	B	A	D	D	D	D	D	B
POTASSIUM CHLORIDE	B	B	A	C	C	C	C	C	B
POTASSIUM HYDROXIDE 10%	B	B	A	C	D	D	D	C	B
POTASSIUM HYDROXIDE 50%	A	A	A	B	C	C	C	B	A
POTASSIUM IODIDE	TB	TB	A	TB	TB	TB	TB	TB	TB
POTASSIUM NITRATE	B	B	A	C	D	D	D	C	B
POTASSIUM PERMANGANATE	A	A	A	TB	TB	TB	TB	TB	A
POTASSIUM PERSULFATE	A	A	A	B	B	B	B	B	A
POTASSIUM SULFATE	B	B	A	C	C	C	C	C	B
PROPIONIC ACID	A	A	A	A	A	A	A	A	A
PROPYLENE GLYCOL	C	C	B	D	D	D	D	D	C
PYRIDINE	A	A	A	A	A	A	A	A	A
SALICYLIC ACID	TB	TB	A	TB	TB	TB	TB	TB	TB
SALT BRINE	C	C	B	D	D	D	D	D	C
SILVER NITRATE	A	A	A	A	TB	TB	TB	A	A
SKYDROL	B	B	A	B	D	C	D	C	B

	Epox-O-Sheen F	Epox-O-Sheen	Ure-Sheen W (VOC Compliant in CA) Clear Only	Epox-O-Sheen 100C (C= Clear; only comes in clear for decorative sys)	Ure-Sheen (not VOC Compliant in CA)	Ure-Sheen CRU (not VOC Compliant in CA)	Ure-Sheen CRU (CA)	Epox-O-Sheen 100P (P= Pigmented, for colored top coats) OR Epox-O-Sheen HS	Shur-Fill (Only to be used under a coating)
SODIUM ACETATE	C	C	B	D	D	D	D	D	C
SODIUM BENZOATE	C	C	B	D	D	D	D	D	C
SODIUM BICARBONATE	C	C	B	D	D	D	D	D	C
SODIUM BISULFITE	TC	TC	TB	TD	TD	TD	TD	TD	TC
SODIUM BISULFATE	B	B	A	C	D	D	D	C	B
SODIUM CARBONATE	B	B	A	C	D	D	D	C	B
SODIUM CHLORATE 50%	A	A	A	TB	TC	TC	TC	TB	A
SODIUM CHLORIDE	B	B	A	B	C	C	C	B	B
SODIUM CHLORITE	A	A	A	A	C	C	C	A	A
SODIUM CHROMATE	A	A	A	B	B	B	B	B	A
SODIUM DICHROMATE	B	B	A	B	B	B	B	B	B
SODIUM FERROCYANIDE	TB	TB	A	TB	TC	TC	TC	TB	TB
SODIUM FLUORIDE	A	A	A	A	A	A	A	A	A
SODIUM HYDROXIDE 10%	C	C	B	E	E	E	E	D	E
SODIUM HYDROXIDE 50%	B	B	B	E	D	D	D	C	D
SODIUM HYPOCHLORITE 3%	A	A	A	A	B	B	B	A	A
SODIUM HYPOCHLORITE 5-15%	A	A	A	A	A	A	A	A	A
SODIUM OXALATE	B	B	A	D	D	D	D	D	B
SODIUM PEROXIDE	B	B	A	C	C	C	C	C	B
SODIUM PHOSPHATE 10%	B	B	A	C	C	C	C	C	B
SODIUM SILICATE	TB	TB	A	TC	TC	TC	TC	TC	TB
SODIUM SULFATE	B	B	A	C	D	D	D	C	B
SODIUM SULFIDE	B	B	A	C	D	D	D	C	B
SODIUM SULFITE	B	B	A	C	D	D	D	C	B
SODIUM TARTRATE	B	B	A	C	D	D	D	C	B
SODIUM THIOSULFATE	B	B	A	C	C	C	C	C	B
STEARIC ACID	A	A	A	B	B	B	B	B	A
STYRENE	A	A	A	B	B	B	B	B	A
SULFAMIC ACID 25%	A	A	A	A	TB	TB	TB	A	A
SULFURIC ACID 10%	B	B	B	C	D	D	D	C	C
SULFURIC ACID 30%	A	A	A	B	C	C	C	B	B
SULFURIC ACID 98%	A	A	A	A	A	A	A	A	A
TALL OIL	B	B	A	C	C	C	C	C	B
TARTARIC ACID	TB	TB	A	TB	TB	TB	TB	TB	TB
TETROCHLOROETHANE	A	A	A	A	B	B	B	B	A
TETRAHYDROFURAN	A	A	A	A	A	A	A	A	A
THIONYL CHLORIDE	A	A	A	A	A	A	A	A	A
TOLUENE	B	B	A	B	C	C	C	B	B
TOLUENE SULFONIC ACID	B	B	A	B	B	B	B	B	B
TOLUIDENE	A	A	A	B	B	B	B	B	A
TRICHLOROACETIC ACID 20%	A	A	A	A	A	A	A	A	A
TRICHLOROETHANE	B	B	A	B	C	C	C	C	A
TRICHLOROETHYLENE	A	A	A	A	TB	TB	TB	A	A
TRICESYL PHOSPHATE TRISODIUM PHOSPHATE	TB	TB	A	TB	TB	TB	TB	TB	TB
TURPENTINE	B	B	A	B	C	C	C	B	B
UREA SOLUTIONS	TB	TB	A	TC	TC	TC	TC	TC	TB
WHITE LIQUOR (PAPER)	TB	TB	A	TB	TC	TC	TC	TB	TB
XYLENE	B	B	A	C	E	D	D	C	B
ZINC CHLORATE	A	A	A	TB	TC	TC	TC	TB	A
ZINC SULFATE	B	B	A	B	C	C	C	B	B

This data is provided as a service of the Paul M. Wolff Co. (PMW) and is believed to be accurate. However this information is neither recommendations by PMW nor product specifications. PMW reserves the right to change or modify data as necessary.